



INSUCIVIL

G / 3000 & 4000

APP MODIFIED BITUMEN MEMBRANE TORCH APPLY
REINFORCED WITH NONWOVEN POLYESTER OR
REINFORCED GLASS FIBER

+ 5°C

Specification		Units	Results	Method of Test	
INSUCIVIL series			G		
Dimensions	Thickness	mm	3 & 4 (±0.2)	ASTM D-5147	
	Length	m	10 (±1%)	UNI 8202	
	Width	m	1 (±1%)	UNI 8202	
	Carrier		Glass fiber	UNI 8202	
Compound	R & B Softening Point		°C	>150	ASTM D-36
	Penetration at	25°C	dm m	20	ASTM D-5
		60°C	dm m	75	ASTM D-5
Membrane	Tensile strength	Longitudinal	N/5cm	350	ASTM D-5147
		Transverse	N/5cm	300	ASTM D-5147
	Elongation	Longitudinal	%	4	ASTM D-5147
		Transverse	%	3	ASTM D-5147
	Tear resistance	Longitudinal	N	200	ASTM D-4073
		Transverse	N	250	ASTM D-4073
	Low temperature flexibility		°C	+5	ASTM D-5147
	High temperature stability		°C	≥110	ASTM D-5147
	Hot running test at 90 slope +90c		mm	<1	UNI 8202
	Water absorption		%	0.2(max)	ASTM D-570
	Moisture content		%	≤1	ASTM D-5147
	Water tightness		Kpa	≥60	EN 1928
	Static puncture resistance			PS2	UNI 8202
	Dynamic puncture resistance			--	UNI 8202
	Dimensional stability after thermal action		%	≤0.2	ASTM D-1204
Aging Due to UV-Radiation		2000 hr	Pass the test	ASTM G-5377	

Methods of application:

INSUCIVIL membranes are designed for easy torch application using a propane torch; it can also apply using mechanical means. Substrates must be thoroughly cleaned and treated with INSUPRIMER cold applied by brush, roller or spray at a rate of 0.2 to 0.3 liters/m². It will depend on substrate Porosity. Membrane must be laid to allow side laps of 8 to 10 cm and end laps of 12 to 15 cm. For more details please contact INSUMAT Technical Services, we will be happy to provide assistance and advice in designing special waterproofing systems. Storage: Sheet rolls shall be stored vertically in a dry place protected from sun and weather. Rolls shall be placed on clean floors or platforms in such a way as to prevent damage to ends and soiling with foreign matters.

NB: 1-The above products data is subject to technical updating without prior notice due to technological research development pursued by INSUMAT.

